



www.tarah.com



Saturated Felt Underlayment

No. 15 ASTM D4869 TYPE I

Width: 39³/₈ inches

Coverage: 432 Sq. Ft per roll

Asphalt Shingle Underlayment.

1. FINISHED WEIGHT AND DIMENSIONS

SPECIFICATION	UNITS	ASTM	TYPICAL
WEIGHT	Lb	34.6 min	35
LENGTH	Ft	131'8-1/2"	131'8-1/2"
WIDTH	In	39-3/8	39-3/8
AREA	Ft ²	432	432

2. COMPOSITION

SPECIFICATION	UNITS	ASTM	TYPICAL
DRY FELT	lb/100ft ²	4.0	4.33
SATURANT	lb/100ft ²	4.0	4.33
SATURATION	%	100	100

3. PERFORMANCE REQUIREMENTS

SPECIFICATION	ASTM	TYPICAL
PLIABILITY AT 77 °F AN 1/2" RADIUS No. OF FAILURES PER TEN STRIPS	0	0
LOSS OF HEATING AT 221 °F FOR 5h max (%)	4	4
TEAR STRENGTH, 77 F, lbf (min) (any direction)	0.44 lbf	0.44 lbf
LIQUID WATER TRANSMISSION TEST	Pass	Pass

4. SAMPLING AND TEST METHODS

ASTM standars

- D146** sampling and testing bitumen saturated felts and woven fabrics for roofing and waterproofing
- D1079** definitions of terms relating to roofing, waterproofing and bituminous materials
- D1922** test method for propagation tear resistance of plastic film and thin sheeting by pendulum method
- E96** test method for water vapor trasnmision of materials

All definitions and terms used in this specification refer to definition D1079.

